

## HOSTAFORM® EC140CF10 | POM | Specialty

### Description

Hostaform® acetal copolymer grade EC140CF10 is a 10% carbon fiber reinforced grade for increase strength, stiffness and electrical conductivity.

Preliminary Data Sheet

Physical properties	Value	Unit	Test Standard
Density	<b>1440</b>	kg/m <sup>3</sup>	ISO 1183
Melt volume rate (MVR)	<b>12</b>	cm <sup>3</sup> /10min	ISO 1133
MVR test temperature	<b>190</b>	°C	ISO 1133
MVR test load	<b>2.16</b>	kg	ISO 1133
Mold shrinkage - parallel	<b>0.8</b>	%	ISO 294-4
Mold shrinkage - normal	<b>1.0</b>	%	ISO 294-4

Mechanical properties	Value	Unit	Test Standard
Tensile modulus (1mm/min)	<b>8500</b>	MPa	ISO 527-2/1A
Tensile stress at break (5mm/min)	<b>70</b>	MPa	ISO 527-2/1A
Tensile strain at break (5mm/min)	<b>1.5</b>	%	ISO 527-2/1A
Flexural modulus (23°C)	<b>8500</b>	MPa	ISO 178
Charpy notched impact strength @ 23°C	<b>3.2</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength @ -30°C	<b>3.2</b>	kJ/m <sup>2</sup>	ISO 179/1eA


Thermal properties	Value	Unit	Test Standard
Melting temperature (10°C/min)	<b>165</b>	°C	ISO 11357-1,-2,-3
DTUL @ 1.8 MPa	<b>158</b>	°C	ISO 75-1/-2
DTUL @ 0.45 MPa	<b>162</b>	°C	ISO 75-1/-2
Coeff.of linear therm. expansion (parallel)	<b>0.3</b>	E-4/°C	ISO 11359-2
Coeff.of linear therm. expansion (normal)	<b>1</b>	E-4/°C	ISO 11359-2

Electrical properties	Value	Unit	Test Standard
Volume resistivity	<b>20</b>	Ohm*m	IEC 60093
Surface resistivity	<b>1000</b>	Ohm	IEC 60093


Test specimen production	Value	Unit	Test Standard
Processing conditions acc. ISO	<b>9988-2</b>	-	Internal

**HOSTAFORM® EC140CF10 | POM | Specialty**


**Stress-strain**



**Secant modulus-strain**



**Typical injection moulding processing conditions**



**Pre Drying:**

Drying is not normally required. If material has come in contact with moisture through improper storage or handling or through regrind use, drying may be necessary to prevent splay and odor problems.

**Drying time: 3 h**

**Drying temperature: 80 - 100 °C**

**Temperature:**

	ϕ Manifold	ϕ Mold	ϕ Melt	ϕ Nozzle	ϕ Zone4	ϕ Zone3	ϕ Zone2	ϕ Zone1
min (°C)	190	80	180	190	190	180	180	170
max (°C)	210	120	200	200	200	190	190	180

## HOSTAFORM® EC140CF10 | POM | Specialty

### Pressure:

	Inj press	Hold press	Back pressure
min (bar)	600	600	0
max (bar)	1200	1200	5

### Speed:

**Injection speed: slow**

## Injection Molding

Standard injection moulding machines with three phase (15 to 25 D) plasticating screws will fit.

Melt temperature	190-230 °C
Mould temperature	80-120 °C

## Contact Information

### Americas

Ticona North American Headquarters  
Product Information Service  
8040 Dixie Highway  
Florence, KY 41042  
USA  
Tel.: +1-800-833-4882  
Tel.: +1-859-372-3244  
email: [prodinfo@ticona.com](mailto:prodinfo@ticona.com)  
Ticona on the web: [www.ticona.com](http://www.ticona.com)

### Customer Service

Tel.: +1-800-526-4960  
Tel.: +1-859-372-3214  
Fax: +1-859-372-3125

### Europe

Ticona GmbH  
Information Service  
Tel.: +49 (0) 180-5842662 (Germany)  
+49 (0) 69-30516299 (Europe)  
Fax: +49 (0) 180-2021202 (Germany & Europe)  
email: [infoservice@ticona.de](mailto:infoservice@ticona.de)  
Internet: [www.ticona.com](http://www.ticona.com)

## General Disclaimer

**NOTICE TO USERS:** Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values.

Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use.

To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication.

Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards.

## HOSTAFORM® EC140CF10 | POM | Specialty

We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed (+49 (0) 69 30516299 for Europe and +1 859-372-3244 for the Americas) for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

The products mentioned herein are not intended for use in medical or dental implants.

© Copyright 2007, Ticona, all rights reserved. (Pub. 26-September-2013)