

HOSTAFORM® LG450UV-D | POM | UV Resistant

Description

Hostaform® acetal copolymer grade LG450UV-D is a specialty grade of acetal copolymer formulated to provide high flow with a reduced gloss finish and a UV stability necessary for interior automotive applications. Hostaform® LG450UV-D is specially suited for intricate applications such as speaker grills.


Physical properties	Value	Unit	Test Standard
Density	1380	kg/m ³	ISO 1183
Melt volume rate (MVR)	32	cm ³ /10min	ISO 1133
MVR test temperature	190	°C	ISO 1133
MVR test load	2.16	kg	ISO 1133
Mold shrinkage - parallel	2.1	%	ISO 294-4
Mold shrinkage - normal	1.9	%	ISO 294-4

Mechanical properties	Value	Unit	Test Standard
Tensile modulus (1mm/min)	2300	MPa	ISO 527-2/1A
Tensile stress at yield (50mm/min)	53	MPa	ISO 527-2/1A
Tensile strain at yield (50mm/min)	8	%	ISO 527-2/1A
Flexural modulus (23°C)	2300	MPa	ISO 178
Charpy notched impact strength @ 23°C	4.0	kJ/m ²	ISO 179/1eA
Charpy notched impact strength @ -30°C	3.5	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
Melting temperature (10°C/min)	167	°C	ISO 11357-1,-2,-3
DTUL @ 1.8 MPa	90	°C	ISO 75-1/-2
DTUL @ 0.45 MPa	152	°C	ISO 75-1/-2
Coeff.of linear therm. expansion (parallel)	1.1	E-4/°C	ISO 11359-2
Coeff.of linear therm. expansion (normal)	1.2	E-4/°C	ISO 11359-2

Test specimen production	Value	Unit	Test Standard
Processing conditions acc. ISO	9988-2	-	Internal

Typical injection moulding processing conditions



HOSTAFORM® LG450UV-D | POM | UV Resistant

Pre Drying:

Predrying is required before processing to ensure a low gloss finish.

Drying time: 3 h

Drying temperature: 105 - 110 °C

Temperature:

	ϕ _{Mold}	ϕ _{Melt}	ϕ _{Nozzle}	ϕ _{Zone4}	ϕ _{Zone3}	ϕ _{Zone2}	ϕ _{Zone1}
min (°C)	80	180	185	180	175	170	170
max (°C)	105	195	195	190	185	180	175

Pressure:

	Inj press	Hold press	Back pressure
min (bar)	600	600	0
max (bar)	1200	1200	5

Speed:

Injection speed: slow

Special Info:

Use slow injection speed until material passes through gate, then increase.

Injection Molding

Standard reciprocating screw injection molding machines with a high compression screw (minimum 3:1 and preferably 4:1) and low back pressure (0.35 Mpa/50 PSI) are favored. Using a low compression screw (I.E. general purpose 2:1 compression ratio) can result in unmelted particles and poor melt homogeneity. Using a high back pressure to make up for a low compression ratio may lead to excessive shear heating and deterioration of the material.

Melt Temperature: Preferred range 182-199 C (360-390 F). Melt temperature should never exceed 230 C (450 F).
 Mold Surface Temperature: Preferred range 82-93 C (180-200 F) especially with wall thickness less than 1.5 mm (0.060 in.). May require mold temperature as high as 120 C (250 F) to reproduce mold surface or to assure minimal molded in stress.
 Wall thickness greater than 3mm (1/8 in.) may use a cooler (65 C/150 F) mold surface temperature and wall thickness over 6mm (1/4 in.) may use a cold mold surface down to 25 C (80 F). In general, mold surface temperatures lower than 82 C (180 F) may hinder weld line formation and produce a hazy surface or a surface with flow lines, pits and other included defects that can hinder part performance.

Contact Information

Americas

Ticona North American Headquarters
 Product Information Service
 8040 Dixie Highway
 Florence, KY 41042
 USA
 Tel.: +1-800-833-4882
 Tel.: +1-859-372-3244
 email: prodinfo@ticona.com
 Ticona on the web: www.ticona.com

Customer Service

Europe

Ticona GmbH
 Information Service
 Tel.: +49 (0) 180-5842662 (Germany)
 +49 (0) 69-30516299 (Europe)
 Fax: +49 (0) 180-2021202 (Germany & Europe)
 email: infoservice@ticona.de
 Internet: www.ticona.com

HOSTAFORM® LG450UV-D | POM | UV Resistant

Tel.: +1-800-526-4960

Tel.: +1-859-372-3214

Fax: +1-859-372-3125

General Disclaimer

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values.

Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use.

To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication.

Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards.

We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed (+49 (0) 69 30516299 for Europe and +1 859-372-3244 for the Americas) for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

The products mentioned herein are not intended for use in medical or dental implants.

© Copyright 2007, Ticona, all rights reserved. (Pub. 26-September-2013)